





8551 8552 8553 9550 V







Lexa

Item number: 25861

Technical Sheet

Width Weight Repeat

Composition Flame retardant

Lightfastness DIN EN ISO 105-B02

Fastness to Washing 40° DIN EN ISO 105-C10

Fabric relaxing washing 40°C DIN EN ISO 6330/DIN EN ISO 5077

Fabric relaxing dry cleaning DIN EN ISO 3175-1

Rub Fastness

DIN EN ISO 105-X12

Scrub resistance Martindale
DIN EN ISO 12947-2 / DIN EN 14465-2006

Pilling DIN EN ISO 12945-2

State: 27.05.2013

Care

approx. 140 cm

approx. 250 g/m²

no repeat

100% Polyester FR

DIN 4102/B1, M1, BS 5867 TYP B, IMO Res. A471 (XII), C1

Flame-resistance is dependant of foam that is used.

note 5-6

note 4-5

warp approx. +/-1%, weft approx. +/-1 %

warp approx. +/-1%, weft approx. +/-1 %

dry: note 4-5, wet: note 4-5

approx. 20000 rubs

note 3-4 at 2000 rubs



The above technical data are average values. These values only describe the technical characteristics and the chemical composition of the delivered goods. Warranties are not given.