830 Switchboard Matting™



- Insulating matting prevents workers from being 'grounded', provides safety in case of electrical shock (not ESD).
- Ozone, flame and oil resistant.
- Can be cut down and will not lose its properties.
- Has to be replaced every 12 months for optimum safety and directly after damaging
- Conforms to ANSI/ASTM D-178
- Free of toxic DOP and DMF.



830 Switchboard Matting™

| | PI | RODUCT SPECIFICATIONS | |
|---------------------------------------|---|--|-----------------------------------|
| Designation | Specialty Matting | | |
| Туре | Electrical protective matting | | |
| Description | Corrugated rib pattern surface Underside has fabric impression | | |
| Material | PVC | | |
| Process | Calendering | | |
| Category | Better | | |
| Recommended use | Near high voltage equipment Maximum usage : 17,000 volts | | |
| Colours | Black | | |
| Weight | 8.4 kg/m ² | | |
| Thickness | 6.4 mm | | |
| Standard sizes | 91 cm x 150 cm 91 cm x 22.8 m | | |
| Custom sizes | N/A | | |
| Special remarks | Has to be replaced every 12 months for optimum safety and directly after damaging | | |
| | 1 | PRODUCT TESTING | 0 0 |
| | Tests | Norms | Results |
| Compression deflection | | U.S. | 100010 |
| dompression deficed | 1.4 kg/cm ² | 0.0. | |
| | 2.8 kg/cm ² | | |
| Foam battery | 2.0 Kg CIII | ASTM D3574 | |
| Abrasion resistance | | ASTM D3374 ASTM D3884-01 | |
| ADIASION TESISLANCE | 500 Cycles | 7/31Wi D3004-01 | |
| | 1000 Cycles | | |
| Static coefficient of fr | | ASTM C1028-96 | |
| Breaking load | | ASTM 0412 | |
| Elongation | | ASTM D412 | 317% |
| Electrical proof | | ASTM D412 ASTM D178-01 Min 20.000 V for 1 min | |
| Dielectric strenght | | ASTM D178-01 Mill 20.000 V 101 1 Mill ASTM D149 Min 30.000 V | Pass |
| Oil resistance | | ASTM D471 | Pass |
| Graves tear strength | | ASTM D 1004 | 2505 PI |
| - | | | |
| Hardness Anti alin | | ASTM D2240-02 | 91 Shore A |
| Anti-slip Electrical Resistance - IBM | | DIN 51130 and BG-RULE BGR181 | |
| | | ASTM F-150 50% Humidity 100 volt | RG 6.6 X 10 ⁹ Ω |
| Static decay | | 101B/NFPA 99 | Pass |
| Flexibility test | | FED-STD-501 | Pass |
| Dimensional stability test | | ASTM D1204 | 0.04 in/ft |
| | | FIRE TESTING | |
| | Critical radiant flux | ASTM E-648 | |
| | Fire retardancy | DIN4102 | |
| | | EN 13501-1 | |
| | Flammability test | ASTM D2859 | Pass |
| | Flame resistance | ASTM D178 | Combustion time 4 min (1.9 in) |
| Sustainability | | Recyclable material Reach Compliant (Registration, Everage Restriction of Chemicals) | aluation, Authorization and |

PRODUCT SPECIFICATIONS

