


PRODUCT DATA SHEET

Collection	SINTEROS Europarquet/Eurostandard
------------	--

1. Product description

3-layer lacquered product made for residential use on dry and flat surface	
Construction	3-strip, 3-layer
Installation	„floating“ or glue down
Thickness (mm)	~ 13,2
Width (mm)	192
Length (mm)	2.272/1.117
Wear layer thickness (mm)	~ 2,8
Weight (kg/m ²)	~ 6,7±10%

2. Construction: 3-layer



Wear layer
Hardwood



Middle layer
Softwood



Bottom layer
Veener

3. Surface protection

UV lacquer



Classic – gloss 30

4. Profile: T-lock



5. Installation

Installation



Disassembling



„Floating“ or glue down installation.
Surface must be clean, dry and flat.
Air humidity: 30-50%.
<http://www.wood.tarkett.rs/CustomerSupport/Documents/Installation%20for%20Wood%20Flooring.pdf>

6. Underfloor heating compatibility*

Since wood is a living material, during the heating season, minor gaps might develop between wood flooring boards due to interior climate conditions. These gaps cannot be related to product quality. Boards movement can be minimized by keeping temperature level at approx. 20° C and a relative air humidity at approx. 50 %.

***Not suitable for the wood species beech and maple**

7. Care and maintenance

Wet mopping or vaccuming



**Wet mopping
with almost dry cloth.**

**Use protective pads when
moving furniture.**

Dry cleaning



Dry mopping Vacuum cleaning

Cleaning

Regular

- **Tarkett Cleaner**



Periodical

- **Tarkett Refresher**





8. Assessment of compliance EN 14342:2005+A1:2008

Feature	Standard	Result
3-layer wood flooring	EN 13489:2002	fulfilled
Lacquered surface feature	EN 14354:2004	fulfilled
Sound reduction	EN ISO 140-8:1997 EN ISO 717-2:1996 / A1:2006	$\Delta L = 17$ dB
Wear layer density	EN 13489:2002	500 – 950 kg/m ³
Reaction to fire	EN 13501-1:2007 +A1:2009	Dfl - S1
Emission of formaldehyde	EN 120:1992	E 1
Slipperiness	CEN/TS 15676:2007	USRV 29
Thermal conductivity	EN 12664:2010	0.11 W/m,K
Biological durability	EN 335-2:2006	Class 1

Date:
14.1.2013.